

BELLO MOS SLATE SERIES

For a classy look with just a hint of sparkle, these highly textured porcelain tiles are an excellent and enduring choice.




WOODBIDGE

Warehouse & Showroom
241 Hanlan Road
Woodbridge, ON, Canada, L4L 3R7
Tel: 905-851-7923
Fax: 905-851-9221

Availability

In Stock Items

Special Order (allow 8-12 weeks)



60x60
24"x24"

MOS SLATE ARGENTO

Specifications

CHARACTERISTICS	TESTS AS PER	TEST RESULTS
Water Absorption (%E)	ISO 10545 - 3 NBR 13818 - anexo: B (AA £ 0,5%)	0,5
Coefficient of Linear Thermal Expansion for 25 at 325°C (°C-1)	ISO 10545 - 8 NBR 13818 - anexo: K	a= 68 ± 2,0 x 10 -7
Modulus of Breaking Strength (MPa)	ISO 10545 - 4 NBR 13818 - anexo: C (Average: ³ 37)	37
Breaking Load (N)	ISO 10545 - 4 NBR 13818 - anexo: C (Average: ³ 1500)	3300
Resistance to Surface Abrasion (PEI) (Class I to V)	ISO 10545 - 7 NBR 13818 - anexo: D	IV
Crazing Resistance	ISO 10545 - 11 NBR 13818 - anexo: F	Resist
Moisture Expansion (mm/m)	ISO 10545 - 10 NBR 13818 - anexo: J	0,10
Frost Resistance	ISO 10545 - 12 NBR 13818 - anexo: M	Resist
Resistance to Thermal Shock	ISO 10545 - 9 NBR 13818 - anexo: L	Resist
Resistance to Stain (Class 1 to 5) * Green staining agent in light oil * Red staining agent in light oil * Iodine * Olive Oil	ISO 10545 - 14 NBR 13818 - anexo: G (Minimum: 3)	- 5 5 5
Chemical Resistance (Class A to C) * Hydrochloric Acid 3% (v/v) * Potassium Hydroxide 30g/l * Citric Acid 100g/l * Lactic Acid 5% (v/v) * Hydrochloric Acid 18% (v/v) * Potassium Hydroxide 100g/l	ISO 10545 - 13 NBR 13818 - anexo: H (Minimum: B)	A A A A A A



BELLO MOS SLATE ARGENTO shown above as wall tile

Shade Variation



Important Note: These samples are not representative of an entire order. The final product may vary slightly in color, luster, and texture. These variations are inherent to natural stone, porcelain, ceramic, and glass tiles. All sizes are approximate.

TORONTO

Designers Walk Bldg. 2
320 Davenport Rd., Suite 105
Toronto, ON, Canada, M5R 1K6
Tel: 416-413-9008
Fax: 416-413-9652

TROY

Michigan Design Center
1700 Stutz Drive, Suite 94
Troy, MI, USA 48084
Tel: 248-643-6520
Fax: 248-643-6523

STERLING HEIGHTS

7515 Nineteen Mile Road
Sterling Heights, MI
USA 48314
Tel: 586-997-1942
Fax: 586-997-1948

www.cercantile.com
mail@cercantile.com