










# INDUSTRY SERIES

This series is inspired by urban design and contemporary architectural trends. Raw represents the interpretation of raw cement and flaking plasters.

## Availability

	30x60	60x60	75x75	25x150	75x150
In Stock Items					
Special Order (allow 8-12 weeks)					
	12"x24"	24"x24"	30"x30"	10"x60"	10"x60"
RAW MIX					
RAW GREY					
RAW LIGHT					
RAW WARM					
OXYDE LIGHT					
OXYDE DARK					
OXYDE RUST					

## Specifications

TEST	REGULATION	REQUIRED STANDARDS	TEST RESULT										
 Water absorption	UNI EN ISO 10545/3	≤ 0,5%	0,20%										
 Sizes	UNI EN ISO 10545/2	<table border="1"> <tr> <td>Length and width</td> <td>± 0,6% max</td> </tr> <tr> <td>Thickness</td> <td>± 5% max</td> </tr> <tr> <td>Linearity</td> <td>± 0,5% max</td> </tr> <tr> <td>Wedging</td> <td>± 0,6% max</td> </tr> <tr> <td>Warpage</td> <td>± 0,5% max</td> </tr> </table>	Length and width	± 0,6% max	Thickness	± 5% max	Linearity	± 0,5% max	Wedging	± 0,6% max	Warpage	± 0,5% max	According
Length and width	± 0,6% max												
Thickness	± 5% max												
Linearity	± 0,5% max												
Wedging	± 0,6% max												
Warpage	± 0,5% max												
 Flexural Strength	UNI EN ISO 10545/4	≥ 35 N/mm <sup>2</sup>	According										
 Deep abrasion resistance	UNI EN ISO 10545/6	≤ 175mm <sup>3</sup>	According										
 Thermal shock resistance	UNI EN ISO 10545/9	No sample must show visible defects	Resistant										
 Frost resistance	UNI EN ISO 10545/12	Resistant	Frost-Proof										
 Chemical resistance (Chemical products for household use and swimming pool additives)	UNI EN ISO 10545/13	-	Resistant										
 Stain resistance	UNI EN ISO 10545/14	GL SMALTATI ≥ 3 UGL Tests method available	According										
 Determination of the anti-slip properties	DIN 51130	R	R9										



### WOODBIDGE

Warehouse & Showroom  
241 Hanlan Road

Woodbridge, ON, Canada, L4L 3R7  
Tel: 905-851-7923  
Fax: 905-851-9221

### TORONTO

Designers Walk Bldg. 2  
320 Davenport Rd., Suite 105  
Toronto, ON, Canada, M5R 1K6  
Tel: 416-413-9008  
Fax: 416-413-9652

### TROY

Michigan Design Center  
1700 Stutz Drive, Suite 94  
Troy, MI, USA 48084  
Tel: 248-643-6520  
Fax: 248-643-6523

### STERLING HEIGHTS

7515 Nineteen Mile Road  
Sterling Heights, MI  
USA 48314  
Tel: 586-997-1942  
Fax: 586-997-1948



RAW MIX

### Shade Variation



**Important Note:** These samples are not representative of an entire order. The final product may vary slightly in color, luster, and texture. These variations are inherent to natural stone, porcelain, ceramic, and glass tiles. All sizes are approximate.

www.cercantile.com  
mail@cercantile.com