

NATURAL SERIES

Stones chosen for their cool, contemporary, and sophisticated palette have been produced into high-performance commercially rated porcelain tiles that exemplify their names.



Availability

In Stock Items



Special Order (allow 8-12 weeks)




Trims

Skirting

10cmx60cm, 4"x23-5/8"

Step Tread with Skirting

33cmx60cmx4cm, 13"x23-5/8"x1-3/4"



FUSSENA
LIPICA VISONE
LIPICA TORTORA
BASALTINA
BRERA BEIGE
BRERA BIANCA
SAVANA

Specifications

TEST	TESTING METHOD	REFERENCE STANDARD	TEST RESULT
Sizes	EN ISO 10545-2	Length and width Thickness Linearity Wedging Warpage Appearance: percentage of acceptable tiles, per lot	±0.6% ±5% ±0.5% ±0.6% ±0.5% 95% min. Conform
Water Absorption %	EN ISO 10545-3	E ≤ 0,5%	average E < 0,1%
Modulus of Rupture	EN ISO 10545-4	35 N/mm ² min.	average ≥ 50 N/mm ²
Breakage Resistance	EN ISO 10545-4	sp. > = 7,5 mm: min 1300 N	average
Scratch Resistance	EN ISO 10545-6	175 mm ³ max.	average < 150 mm ³
Thermal Expansion Coefficient	EN ISO 10545-8	Testing method available	6,2 MK ⁻¹
Thermal Shock Resistance	EN ISO 10545-9	Testing method available	Resistant
Frost Resistance	EN ISO 10545-12	Required	Resistant
Resistance to Low Concentrations of Acids and Alkali	EN ISO 10545-13	See manufacturer's declaration	Resistant
Resistance to High Concentrations of Acids and Alkali	EN ISO 10545-13	Testing method available	Resistant
Resistance to Domestic Chemicals and Additives for Swimming Pools	EN ISO 10545-13	UB min.	UA
Stain Resistance of Unglazed Matte Porcelain	EN ISO 10545-14	Testing method available	Resistant
Colour Resistance to Light	DIN 51094	No noticeable color change.	No alteration after testing



NATURAL FUSSENA

Shade Variation



LOW

Important Note: These samples are not representative of an entire order. The final product may vary slightly in color, luster, and texture. These variations are inherent to natural stone, porcelain, ceramic, and glass tiles. All sizes are approximate.

WOODBIDGE

Warehouse & Showroom
241 Hanlan Road
Woodbridge, ON, Canada, L4L 3R7
Tel: 905-851-7923
Fax: 905-851-9221

TORONTO

Designers Walk Bldg. 2
320 Davenport Rd., Suite 105
Toronto, ON, Canada, M5R 1K6
Tel: 416-413-9008
Fax: 416-413-9652

TROY

Michigan Design Center
1700 Stutz Drive, Suite 94
Troy, MI, USA 48084
Tel: 248-643-6520
Fax: 248-643-6523

STERLING HEIGHTS

7515 Nineteen Mile Road
Sterling Heights, MI
USA 48314
Tel: 586-997-1942
Fax: 586-997-1948

www.cercantile.com
mail@cercantile.com