

## REFLECTIONS COLLECTION

40x120cm | 16x48in



STANDARD	CHARACTERISTICS		TEST RESULT
<b>UNE-EN ISO 10545-3</b>	Water absorption		E > 10%
<b>UNE-EN ISO 10545-4</b>	Breaking strength (N)		1000
<b>UNE-EN ISO 10545-4</b>	Modulus of rupture (N/mm <sup>2</sup> )		17
<b>UNE-EN ISO 10545-6</b>	Resistance to deep abrasion (mm <sup>3</sup> )		
<b>UNE-EN ISO 10545-7</b>	Abrasion resistance		
	Class		
	Stage		Rev.
<b>UNE-EN ISO 10545-9</b>	Thermal shock resistance		
<b>UNE-EN ISO 10545-11</b>	Resistance to crazing		O.k.
<b>UNE-EN ISO 10545-12</b>	Frost Resistance		
<b>UNE-EN ISO 10545-13</b>	<b>Chemical Resistance</b>		
	Household Chemicals		A
	Swimming pool salts		A
	Citric Acid		LA
	Lactic Acid		
	Hydrochloric Acid low concentrations		LA
	Hydrochloric Acid high concentrations		
	Potassium Hydroxide low concentrations		LA
Potassium Hydroxide high concentrations			
<b>UNE-EN ISO 10545-14</b>	<b>Resistance to staining</b>		
	Fe <sub>2</sub> O <sub>3</sub> / Cr <sub>2</sub> O <sub>3</sub>		Class 5
	Iodine / alcohol solution		Class 5
	Light oil		Class 5
<b>UNE-41901:2017 EX</b>	Slip Resistance		
<b>Dimension (mm)</b>	398x1198	<b>Thickness (mm)</b>	10,9
<b>Classification according to Saloni quality:</b>			