


SAND COLLECTION

Dry - Pressed Ceramic Tiles ISO 13006 Annex G - UNI EN 14411 Annex G - Bla UGL e GL

CARATTERISTICHE TECNICHE Technical Features - Caracteristiques Techniques - Technische Eigenschaften Technische Eigenschaften - Características Técnicas - Технические Характеристики		NORMA Standard - Norme Norm - Norma - Норма	VALORI Value - Valeur Vorgabe - Valor - Средние			
	PLANARITÀ Flatness - Planéité - Ebenflächigkeit - Planiyud - Плоскостность	UNI EN ISO 10545/2	± 0,26% / ± 1,5mm			
		ASTM C485 WARPAGE	-			
		CALIBRATED ± 0,75% (MAX ± 0,09 IN)	-			
		RECTIFIED ± 0,40% (MAX ± 0,05 IN-SIZE ≤ 60cm) (MAX ± 0,07 IN-SIZE > 60cm)	± 0,25% (MAX ± 0,05 IN-SIZE ≤ 60cm) (MAX ± 0,07 IN-SIZE > 60cm)			
	ASSORBIMENTO D'ACQUA (VALORE MEDIO IN %) Water absorption (Average value expressed in %) - Absorption d'eau (Valeur moyenne en %) Wasseraufnahme (Durchschnittswert in %) - Absorción de agua (Valor medio en %) Поглощение воды	UNI EN ISO 10545/3 ≤ 0,5 %	CONFORME			
		ASTM C373	COMPLIANT			
	RESISTENZA ALLA FLESSIONE Modulus of rupture - Resistance a la flexion - Biegefestigkeit Resistencia a la flexion - Прочность на изгиб		NAT.	20MM		
		UNI EN ISO 10545/4	≥ 50 N/mm²	≥ 50 N/mm²		
	FORZA DI ROTTURA Breaking strength - Résistance à la rupture - Bruchlast - Resistencia a la rotura - Разрывное усилие	UNI EN ISO 10545/4 ASTM C648	≥ 2000 N 700 LBS	≥ 4000 N 700 LBS		
	RESISTENZA AL GELO Frost resistance - Résistance au gel - Frostbeständigkeit Resistencia a las heladas - Морозостойкость	UNI EN ISO 10545/12 ASTM C1026	CONFORME UNAFFECTED			
	RESISTENZA CHIMICA AD ALTE E BASSE CONCENTRAZIONI DI ACIDI E BASI Chemical resistance to high and low acid and basic concentrations Résistance chimique aux hautes et basses concentrations d'acides et de bases Chemikalienfestigkeit bei hohen und niedrigen Konzentrationen von Säuren und Basen Resistencia química con concentraciones altas y bajas de ácidos y bases Химическая стойкость к высоким и низким концентрациям кислот и щелочей		Sand 32x32	Sand Strie 12x48		
		UNI EN ISO 10545/13 ASTM C-650	ULA - ULA - UA UNAFFECTED	GA - GLA - GHA UNAFFECTED		
	RESISTENZA ALLE MACCHIE Stain resistance - Résistance aux taches - Fleckenbeständigkeit Resistencia a las manchas - Стойкость к образованию пятен	UNI EN ISO 10545/14 CTI 81-7D	5 NO EVIDENT VARIATION			
	COEFFICIENTE DI ATTRITO Slip resistance - Coefficient de glissement - Rutschfestigkeit Barfußbereich Coeficiente de atrito medio - Коэффициент трения		NAT.	LAPP.	ANTISLIP	20MM
		DIN 51130	R10	-	R11	R11
		DIN 51097	B (A+B)	-	C (A+B+C)	C (A+B+C)
		ANSI A 137.1- 2012 DCOF (SECTION 9.6)	DRY ≥ 0,42 WET ≥ 0,42	-	DRY ≥ 0,42 WET ≥ 0,42	DRY ≥ 0,42 WET ≥ 0,42
		B.C.R.A.	≥ 0,40	-	≥ 0,40	≥ 0,40



TORONTO
115 Carnarvon Street
Toronto, ON M6M 3C9
T 416 413 9008
F 416 413 9652

TROY
1700 Stutz Drive, Ste 92 & 94
Troy, MI 48084
T 248 643 6520
F 248 643 6523

Please note, all specifications have been supplied
by the manufacturer and are subject to change.

Email: mail@cercantile.com
Website: www.cercantile.com