



## ITALIAN COLLECTION

**Model/ Series:** Italian Carrara White Polished 24x48, 48x48  
**Size:** All Sizes  
**Colors:** All Colors Available  
**Type:** POLISHED PORCELAIN  
**Application:** INDOOR  
**Thickness:** 7 mm  
**Recycled Content:** 9% \*Pre-Consumer

### Technical Data

	ASTM Test	ISO Test	Value Required ANSI	Declared ASTM
Water Absorption	C373	ISO-10545/3	<=0.5%	<=0.5%
Break Strength	C648	ISO-10545/4	>= 250	Min. 250
Scratch Hardness	MOH's Scale	EN-101	-	4
Chemical Resistance	C650	ISO-10545/13	Unaffected	Unaffected
Frost Resistance	C1026	ISO-10545/12	Resistant	Resistant
Group	SEE FAQs	SEE FAQs	-	4P
Deep Abrasion - Unglazed Tiles	C1243	ISO-10545/6	<175 mm <sup>3</sup>	-
PEI - Glazed Tiles***	C1027	ISO-10545/7	-	4
Minimum Bond Strength (PSI)	C482		>=50 psi	165
Dynamic Coefficient of Friction (DCOF)	A137.1	-	>=0.42	<=0.27
Shade and Texture Rating	CTDA "V"	-	-	V3
Facial Dimensions	C499	ISO-10545/2	1.5% Max	Pass
Range of Thickness	C499	ISO-10545/2	0.040 Max	Pass
Warpage	C485	ISO-10545/2	0.75%	Pass
Wedging	C502	ISO-10545/2	1.0% Max	Pass

**Model/ Series:** Italian Carrara White Matte 48x48  
**Size:** All Sizes  
**Colors:** All Colors Available  
**Type:** GLAZED PORCELAIN  
**Application:** INDOOR  
**Thickness:** 7 mm  
**Recycled Content:** 9% \*Pre-Consumer

### Technical Data

	ASTM Test	ISO Test	Value Required ANSI	Declared ASTM
Water Absorption	C373	ISO-10545/3	<=0.5%	<=0.5%
Break Strength	C648	ISO-10545/4	>= 250	Min. 250
Scratch Hardness	MOH's Scale	EN-101	-	4
Chemical Resistance	C650	ISO-10545/13	Unaffected	Unaffected
Frost Resistance	C1026	ISO-10545/12	Resistant	Resistant
Group	SEE FAQs	SEE FAQs	-	4
Deep Abrasion - Unglazed Tiles	C1243	ISO-10545/6	<175 mm <sup>3</sup>	-
PEI - Glazed Tiles***	C1027	ISO-10545/7	-	4
Minimum Bond Strength (PSI)	C482		>=50 psi	165
Dynamic Coefficient of Friction (DCOF)	A137.1	-	>=0.42	<=0.33
Shade and Texture Rating	CTDA "V"	-	-	V3
Facial Dimensions	C499	ISO-10545/2	1.5% Max	Pass
Range of Thickness	C499	ISO-10545/2	0.040 Max	Pass
Warpage	C485	ISO-10545/2	0.75%	Pass
Wedging	C502	ISO-10545/2	1.0% Max	Pass

TORONTO  
 115 Carnarvon Street  
 Toronto, ON M6M 3C9  
 T 416 413 9008  
 F 416 413 9652

TROY  
 1700 Stutz Drive, Ste 92 & 94  
 Troy, MI 48084  
 T 248 643 6520  
 F 248 643 6523

Please note, all specifications have been supplied by the manufacturer and are subject to change.

Email: mail@cercantile.com  
 Website: www.cercantile.com



## ITALIAN COLLECTION

**Model/ Series:** Italian Extra White Polished 48x48  
**Size:** All Sizes  
**Colors:** All Colors Available  
**Type:** POLISHED PORCELAIN  
**Application:** INDOOR  
**Thickness:** 7 mm  
**Recycled Content:** 9% \*Pre-Consumer

### Technical Data

	ASTM Test	ISO Test	Value Required ANSI	Declared ASTM
Water Absorption	C373	ISO-10545/3	<=0.5%	<=0.5%
Break Strength	C648	ISO-10545/4	>= 250	Min. 200
Scratch Hardness	MOH's Scale	EN-101	-	4
Chemical Resistance	C650	ISO-10545/13	Unaffected	Unaffected
Frost Resistance	C1026	ISO-10545/12	Resistant	Resistant
Group	SEE FAQs	SEE FAQs	-	3
Deep Abrasion - Unglazed Tiles	C1243	ISO-10545/6	<175 mm <sup>3</sup>	-
PEI - Glazed Tiles***	C1027	ISO-10545/7	-	3
Minimum Bond Strength (PSI)	C482		>=50 psi	165
Dynamic Coefficient of Friction (DCOF)	A137.1	-	>=0.42	<0.40
Shade and Texture Rating	CTDA "V"	-	-	V3
Facial Dimensions	C499	ISO-10545/2	1.5% Max	Pass
Range of Thickness	C499	ISO-10545/2	0.040 Max	Pass
Warpage	C485	ISO-10545/2	0.75%	Pass
Wedging	C502	ISO-10545/2	1.0% Max	Pass

**Model/ Series:** Italian Extra White Matte 48x48  
**Size:** All Sizes  
**Colors:** All Colors Available  
**Type:** GLAZED PORCELAIN  
**Application:** INDOOR  
**Thickness:** 7 mm  
**Recycled Content:** 9% \*Pre-Consumer

### Technical Data

	ASTM Test	ISO Test	Value Required ANSI	Declared ASTM
Water Absorption	C373	ISO-10545/3	<=0.5%	<=0.5%
Break Strength	C648	ISO-10545/4	>= 250	Min. 200
Scratch Hardness	MOH's Scale	EN-101	-	5
Chemical Resistance	C650	ISO-10545/13	Unaffected	Unaffected
Frost Resistance	C1026	ISO-10545/12	Resistant	Resistant
Group	SEE FAQs	SEE FAQs	-	4
Deep Abrasion - Unglazed Tiles	C1243	ISO-10545/6	<175 mm <sup>3</sup>	-
PEI - Glazed Tiles***	C1027	ISO-10545/7	-	3
Minimum Bond Strength (PSI)	C482		>=50 psi	165
Dynamic Coefficient of Friction (DCOF)	A137.1	-	>=0.42	<0.40
Shade and Texture Rating	CTDA "V"	-	-	V3
Facial Dimensions	C499	ISO-10545/2	1.5% Max	Pass
Range of Thickness	C499	ISO-10545/2	0.040 Max	Pass
Warpage	C485	ISO-10545/2	0.75%	Pass
Wedging	C502	ISO-10545/2	1.0% Max	Pass

TORONTO  
 115 Carnarvon Street  
 Toronto, ON M6M 3C9  
 T 416 413 9008  
 F 416 413 9652

TROY  
 1700 Stutz Drive, Ste 92 & 94  
 Troy, MI 48084  
 T 248 643 6520  
 F 248 643 6523

Please note, all specifications have been supplied by the manufacturer and are subject to change.

Email: mail@cercantile.com  
 Website: www.cercantile.com



## ITALIAN COLLECTION

**Model/ Series:** Italian Statuary White 24x48  
**Size:** All Sizes  
**Colors:** All Colors Available  
**Type:** GLAZED PORCELAIN  
**Application:** INDOOR  
**Thickness:** 10 mm (35x35, 24x48), 9mm (24x24), 8.5mm (12x24)  
**Recycled Content:** 5% \*Pre-Consumer

### Technical Data

	ASTM Test	ISO Test	Value Required ANSI	Declared ASTM
Water Absorption	C373	ISO-10545/3	<=0.5%	<=0.5%
Break Strength	C648	ISO-10545/4	>= 250	Min. 335
Scratch Hardness	MOH's Scale	EN-101	-	5
Chemical Resistance	C650	ISO-10545/13	Unaffected	Unaffected
Frost Resistance	C1026	ISO-10545/12	Resistant	Resistant
Group	SEE FAQS	SEE FAQS	-	4
Deep Abrasion - Unglazed Tiles	C1243	ISO-10545/6	<175 mm <sup>3</sup>	Pass
PEI - Glazed Tiles***	C1027	ISO-10545/7	-	5
Minimum Bond Strength (PSI)	C482		>=50 psi	165
Dynamic Coefficient of Friction (DCOF)	A137.1	-	>=0.42	>=0.42
Shade and Texture Rating	CTDA "V"	-	-	V3
Facial Dimensions	C499	ISO-10545/2	1.5% Max	Pass
Range of Thickness	C499	ISO-10545/2	0.040 Max	Pass
Warpage	C485	ISO-10545/2	0.75%	Pass
Wedging	C502	ISO-10545/2	1.0% Max	Pass

TORONTO  
 115 Carnarvon Street  
 Toronto, ON M6M 3C9  
 T 416 413 9008  
 F 416 413 9652

TROY  
 1700 Stutz Drive, Ste 92 & 94  
 Troy, MI 48084  
 T 248 643 6520  
 F 248 643 6523

Please note, all specifications have been supplied by the manufacturer and are subject to change.

Email: [mail@cercantile.com](mailto:mail@cercantile.com)  
 Website: [www.cercantile.com](http://www.cercantile.com)