















The Lakeside Collection

Legenda/Legend/Légende/Legende/Leyenda
Gres Fine Porcellanato – EN 14411 ISO 13006 Gruppo Bla Annex G

	Regulation	Required standards	Refin Value
 Dimensioni/Size/Dimensions/ Abmessungen/Åmningarna/ Dimensiones	UNI EN ISO 10645/2	Non verificato Not verified Rectified Rectifié	Conforme Compliant
		Lunghezza e larghezza/Length and width/Longueur et largeur/Longo ur e lățime/Angrößen/ Lunghezza e larghezza/Length and width/Longueur et largeur/Longo ur e lățime/Angrößen	±0.6% max 2mm ±0.3% max 1mm
		Spessore/Thickness/Epaisseur/ Stärke/Dicke/Grosor	±0.5% max 0.5mm ±0.5% max 0.5mm
		Rettilineità spigoli/Inequality/ Rectitude des arêtes/ Kantenperichkeit/Flechtheit/kanten/ Rectitud de los lados	±0.5% max 1.5mm ±0.3% max 0.8mm
		** Ortogonalità/Wedging/ Orthogonalität/Rectangularité/ Haakrecht/Hoeken/Ortogonalidad	±0.6% max 2mm ±0.3% max 1.5mm
		Pianità/Warpage/Planité/ Ebenheit/Planität/ Valuedad/Planitud	±0.5% max 2mm ±0.1% max 1.8mm
	* According to ISO 13006		
 Assorbimento acqua / Water absorption / Absorption d'eau / Wasseraufnahme / Waterabsorptie / Absorción de agua	UNI EN ISO 10645/3	≤ 0.5 %	0.2%
 Resistenza alla flessione / Flexural Strength/Resistance à la flexion / Biegefestigkeit / Bujgræstheid / Resistencia a la flexión	UNI EN ISO 10645/4	≥ 35 N/mm ² S ≥ 1300 N (thickness ≥ 7.5 mm)	Conforme Compliant
 Coefficiente di restituzione (COR) / Coefficient of restitution (COR) / Coefficient de restitution (COR) / Restitutionskoeffizient (COR) / Restitucióncoefficient (COR)	UNI EN ISO 10645/5	Valore consigliato ≥ 0.55/ Recommended value ≥ 0.55/ Valeur recommandée ≥ 0.55/ Empfohlener Wert ≥ 0.55/ Aprobación recomendada ≥ 0.55/ Relativ recommended ≥ 0.55	Conforme Compliant
 Resistenza all'abrasione profonda / Deep abrasion resistance / Resistance à l'abrasion / Widerstand gegen Tiefverschleiß / Weerstand tegen afschuren / Resistencia a la abrasión profunda	UNI EN ISO 10645/6	≤ 175 mm ³	Conforme Compliant
 Resistenza all'abrasione/ Abrasion resistance / Resistance a l'abrasion / Abriebwiderstand / Weerstand tegen afschuren / Resistencia a la abrasión	UNI EN ISO 10645/7	FS Solo per piastrelle smaltate / Only for glazed tiles	vedere interno See inside
 Coefficiente di dilatazione termica lineare / Coefficient of thermal linear expansion / Coefficient de dilatation thermique linear / Lineare Wärmeausdehnungskoeffizient / Lineaire thermische uitzetting / Coeficiente de dilatación termica lineal	UNI EN ISO 10645/8	Metodo di prova disponibile / Test method available / Methode disponible / Verfügbare / Lieferfähig / Testmethode beschikbaar / Método de prueba disponible	≤ 7 10 ⁻⁴ C ⁻¹
 Resistenza agli sbalzi termici / Thermal shock resistance / Resistance aux écarts de température / Temperaturwechselbeständigkeit / Resistencia al choque térmico	UNI EN ISO 10645/9	Nessuna campione deve presentare difetti visibili. No sample must show visible defects / Aucun échantillon ne doit présenter des défauts visibles / Kein Exemplar darf sichtbare Schäden aufweisen / Geen enkel monster mag zichtbare gebeuren vertonen / Ninguna muestra debe presentar defectos visibles	Conforme Compliant
 Dilatazione all'umidità / Moisture expansion / Dilatación a l'humiditat / Feuchtigkeitssausdehnung / Uitzetting door vocht / Dilatación por la humedad	UNI EN ISO 10645/10	Metodo di prova disponibile / Test method available / Methode disponible / Verfügbare / Lieferfähig / Testmethode beschikbaar / Método de prueba disponible	≤ 0.01 % (3.1 mm/m)
 Resistenza al fuoco / Fire resistance / Resistance au feu / Brandverhalten / Brandweerstand / Resistencia al fuego	UNI EN ISO 13501-1	Dichiarare un valore / Declare a value Classe A1 oppure A ₁ / Class A1 or A ₁	A ₁
 Resistenza al gelo / Frost resistance / Resistencia au gel / Frostbeständigkeit / Vorstbeständigkeit / Resistencia a la helada	UNI EN ISO 10645/12	Resistent/Resistent / Resistentes / Widerstandsfähig / Widerstandig / Resistentes	Conforme Compliant

Legenda/Legend/Légende/Legende/Leyenda
Gres Fine Porcellanato – EN 14411 ISO 13006 Gruppo Bla Annex G

	Regulation	Required standards	Refin Value
 Resistenza all'attacco chimico / Chemical resistance / Resistance à l'attaque chimique / Beständigkei t gegen Chemikalien / Chemische bestandheid / Resistencia al ataque químico	UNI EN ISO 10645/13	Resistenza al prodotto chimico di uso domestico ed agli additivi per piscine / Resistance to household chemicals and swimming pool salts	UNI EN ISO 10645/13
		Resistenza a basse concentrazioni di acidi e alcali / Resistance to low concentrations of acids and alkalis	UNI EN ISO 10645/13
		Resistenza ad alte concentrazioni di acidi e alcali / Resistance to high concentrations of acids and alkalis	UNI EN ISO 10645/13
 Resistenza alle macchie / Stain resistance / Insensibilité aux taches / Beständigkeit gegen Fleckenfleber / Dubstansen / Weerstand tegen vlekken / Resistencia a las manchas	UNI EN ISO 10645/14	UGL Dichiarare un valore / UGL Declare a value GL ≥ 3	vedere interno See inside
 Decolorazione piombo e cadmio/ Lead and cadmium discharge/ Partie de plomb et cadmium/ Abgabe von Blei und Cadmium/ Ditbaar van lood en cadmium/ Cesión de plomo y cadmio	UNI EN ISO 10645/15	Valore dichiarato per piastrelle GL / Declared value for GL tiles	vedere interno See inside
 Indicazione di resistenza allo scivolamento / Assessment of slip resistance / Indication de la résistance au glissement / Bestimmung der Trittsicherheits / Indicatie voor de slipvastheid / Indicación de resistencia al deslizamiento	DIN 51130 DIN 51097 BS 10165-2:2002 (EN 13015: 10165) Annex C Pendulum Friction Test	Dichiarare un valore (R) / Declare a value (R) Dichiarare un valore (A+B+C) / Declare a value (A+B+C) Dichiarare un valore / Declare a value	vedere interno See inside vedere interno See inside vedere interno See inside
 Coefficiente di attrito dinamico / Measurement of dynamic coefficient of friction / Mesure du coefficient de frottement dynamique / Meting van dynamische wrijvingscoëfficiënt / Coeficiente de rozamiento dinámico	BCRA Rap CECR81 AEN 01.07.1 2012(B073000)	Asciutto > 0.40 / Bagnato > 0.40 > 0.42 Wet	vedere interno See inside

Shade Variation: V3

*Per piastrelle rettangolari che abbiano lato maggiore L ≥ 60 cm a rapporto tra lati 1:1, la misurazione della ortogonalità deve venire condotta solo sui loro corti.
For oblong tiles with L ≥ 60 cm and ratio length/width L/W ≥ 3, measurement of rectangularity only on short edges.

TORONTO
115 Carnarvon Street
Toronto, ON M6M 3C9
T 416 413 9008
F 416 413 9652

TROY
1700 Stutz Drive, Ste 92 & 94
Troy, MI 48084
T 248 643 6520
F 248 643 6523

Please note, all specifications have been supplied
by the manufacturer and are subject to change.

Email: mail@cercantile.com
Website: www.cercantile.com